

# SG IR70

| OPTICAL PROPERTIES | | Clear glass |
|---|---|---|
| Visible Light | Transmitted | 72% |
| Visible Light Reflected | External | 9% |
| | Internal | 9% |
| IR Rejection | | 85% |
| UV Rejected | | 99% |
| Total Solar Energy Rejected (TSER) | | 52% |
| Solar Heat Gain Coefficient (G value) | | 0.48 |

SAINT-GOBAIN

Grindwell Norton Limited
Devanahalli Road
Off Old Madras Road
Bengaluru - 560049